

Crafty Source

Make it your own

You can press using a heat press using the setting detailed below or you can use domestic iron, set to the hottest cotton setting with no steam and press for few seconds of application time.

### HTV Hot Flex

Heat press	160°C
Press for	15 seconds
Peel	Hot/warm peel

Suitable for Polyester and Cotton

### TeckWrap

Heat press	150°C to 160°C
Press for	8-12 seconds
Peel	Warm/cool peel

Suitable for Polyester and Cotton

### HTV Sparkle, Glitter & Chrome

Heat press	160°C
Press for	15 seconds
Peel	Warm/cool peel

Suitable for Polyester and Cotton

### HTV Flex and Neon

Heat press	150°C
Press for	15 seconds
Peel	Warm/cool peel

Suitable for Polyester and Cotton

### HTV Patterned (Artflex)

Heat press	160°C
Press for	15 seconds
Peel	Cool peel

Suitable for Polyester and Cotton